



ELECTRICAL INSULATION MATERIALS

Electrical Insulation Crepe Paper



PRODUCT PARAMETERS

Standard: JB/T 10441.3-2004

No.	Properties		Unit	Base Paper Thickness		
				0.05mm	0.075mm	0.13mm
1	Thickness Of Crepe Paper		Mm	0.35±0.05	0.38±0.08	0.70-0.90
2	Ash Content		%	≤0.7	≤0.7	≤0.8
3	Moisture Content		%	≤7.0	≤7.0	≤8.0
4	Water Extraction PH		-	6.0-8.0		
5	Oil Contamination		%	<0.1		
6	Tensile Strength	MD	N	30	40	50
		CD	N	20	30	40
7	Oil Absorption Height	MD	Mm/10min	≥7.0		
			Mm/60min	≥30.0		
		CD	Mm/10min	≥20.0		
			Mm/60min	≥50.0		
8	Crepe Ratio		%	50		
9	Power Frequency Breakdown Voltage		V/Layer	≥950	≥1000	≥1000
10	Conductivity		Ms/M	-	-	≤10
11	Appearance Density		G/M ²	60±10%	110±10%	120-150



CONTACT INFO

Tel: +86 13137718313

Email: info@ztelecgroup.com

Add: #14 ZTaero Building,
Uni-science Park, Zhengzhou,
Henan,China